

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

## TEST REPORT

Client : Aventino Gr Unit 1/27 Le Rhodes NS		S	Test Numbe Issue Date Print Date	r : : :	19-00676 25/03/202 25/03/202	20
Sample Description	Engineered Flooring Colour : Oak End Use : Flooring	sity : Approx	Oak Flooring" ed to a multi layer ply 12.4kg/m2	ywood	3	
ISO 9239.1-2003	Reaction to Fire Tests for Floorin	ngs. Determinati	on of the Burning B	ehavi	our using a	
	Radiant Heat Source					
	Radiant Heat Source Date of Sample Arrival		15/11/2019			
			15/11/2019 25/03/2020			
	Date of Sample Arrival	1		3	Mean	
	Date of Sample Arrival Date Tested	1 4.8	25/03/2020	3	Mean -	kW/m²
	Date of Sample Arrival Date Tested CHF Value	-	25/03/2020 2 -	3 - .4		kW/m² kW/m²
	Date of Sample Arrival Date Tested CHF Value Length	4.8	25/03/2020 2 -	-	-	
	Date of Sample Arrival Date Tested CHF Value Length Width	4.8 4.0	25/03/2020 2 - 4.4 4	4	- 4.3	
	Date of Sample Arrival Date Tested CHF Value Length Width HF-30 Value	4.8 4.0	25/03/2020 2 - 4.4 4	4	- 4.3 Mean -	kW/m²
	Date of Sample Arrival Date Tested CHF Value Length Width HF-30 Value Length	4.8 4.0 1	25/03/2020 2 - 4.4 4 2 -	4	- 4.3 Mean -	kW/m² kW/m²
	Date of Sample Arrival Date Tested CHF Value Length Width HF-30 Value Length Width	4.8 4.0 1 - 4.0	25/03/2020 2 - 4.4 4 2 - 4.4	3	- 4.3 Mean -	kW/m² kW/m²

Yes

Page 1 of 2

198398

40596

Blistering

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing Mechanical Testing - Performance & Approvals Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

: Accreditation No : Accreditation No. : Accreditation No

983 985 1356



HAEL A. JACKSON B.Sc.(Hons) MIC MANAGING DIRECTOR



APPROVED SIGNATORY

(C)



Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

## **TEST REPORT**

Client :	Aventino Group Pty Ltd T/AS Wonderwood Floors	Test Number	:	19-006761
	Unit 1/27 Leeds Street	Issue Date	:	25/03/2020
	Rhodes NSW 2138	Print Date	:	25/03/2020

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

HF30 not reported as flame out time occurred before 30 minutes.

198398

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved

40596



the Managing Director of AWTA Ltd.

Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing - Mechanical Testing - Performance & Approvals Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by

: Accreditation No. : Accreditation No. : Accreditation No.

No. 983 No. 985 No. 1356 AWT

Page 2 of 2





C

APPROVED SIGNATORY