

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client :	Aventino Group Pty Ltd T/AS Wonderwood Floors	Test Number	:	21-003049
	Unit 1/27 Leeds Street	Issue Date	:	18/08/2021
	Rhodes NSW 2138	Print Date	:	20/08/2021

Sample Description	Hybrid flooring planks with Colour : Timber effect End Use : Flooring	t 7mm Limestone		-				
AS ISO 9239.1-2003	Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source							
	Date of Sample Arrival			16-06-2021				
	Date Tested			18-08-2021				
	CHF Value		1	2	3	Mean		
	Length		10.3	10.3	9.9	10.2	kW/m²	
	Width		10.6	-	-	-	kW/m²	

246616

C Australian Wool Testing Authority Ltd Copyright - All Rights Reserved Accredited for compliance with ISO/IEC 17025 - Testing




Smoke Value

Length

Width

52372

Blistering



1

40

34

2

62

_

3

44

_

Mean

49

_

Yes

Page 1 of 2

%.min

%.min

12





MIC (



Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client :	Aventino Group Pty Ltd T/AS Wonderwood Floors
	Unit 1/27 Leeds Street
	Rhodes NSW 2138

Test Number	:	21-003049
Issue Date	:	18/08/2021
Print Date	:	20/08/2021

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

Each specimen was clamped to a substrate of 6mm thick fibre reinforced cement board prior to testing.

HF30 not reported as flame out time occurred before 30 minutes.

Each specimen was loose laid over 6mm thick fibre reinforced cement board and clamped prior to testing.

246616

52372

 Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



NATA

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

12

Fiona McDonald APPROVED SIGNATORY





MICHAEL A. JACKSON B.Sc.(Hons)

C